## PHYSICAL TESTING REPORT



insight creating advantage



Mactac UK

37 Tenter Road Moulton Park Northampton Northamptonshire NN3 6AY

Mr. Douglas Spencer FAO:

Report of Tests on: Self adhesive textured laminate

Your Reference: **LUV 6300** 

**Lucideon Reference: (154373)-24632** 

**Date Reported:** Date Logged:

15-Oct-2015

Order Number:

Date(s) of Test(s):

PO 5012

14-Oct-2015 to 14-Oct-2015

12-Oct-2015

Inclined Platform Test for Slip Resistance In Shod Conditions

DIN 51130:2010

	Operator 1 - Angle of Inclination	Operator 2 - Angle of Inclination
No.	•	٥
1	6.1	6.3
2	5.5	5.9
3	5.8	6.5

Description of Test Specimen(s): 2 textured laminate boards

Average of Six Shod Results (Corrected): 6.0 °

Category: R9

The critical angle awhich a test person reaches the limit of safe walking on an inclined plane is used as a measure of slip resistance.

Opinions and interpretations expressed herein are outside the scope of UKAS Accreditation.

**End of Test Report** 

