

MACal® 9800 HT PRO

Technical Data Sheet

PRODUCT DESCRIPTION

MACal 9800 HT PRO are premium polymeric stabilized calendered soft vinyl films coated with a durable permanent high tack adhesive giving excellent dimensional stability. MACal 9800 HT PRO is designed for trouble-free computer cutting and fast weeding for difficult substrates

CONSTRUCTION

Face material :

Polymeric stabilized calendered vinyl, 66 µm thick, cadmium-free.

Adhesive :

High quality clear solvent based high tack permanent acrylic adhesive.

Liner :

Highly stable 135 gsm white kraft paper with blue backprinting.

For white vinyl the liner is coated with a blue silicone coating to improve the contrast with the film colour.

NB : **CONTRAST B** ensures a clear view during the stripping process therefore improving productivity.

TYPICAL USES

MACal 9800 HT PRO is designed for long term interior and exterior marking applications (POS, wall signs...) on non-smooth or slightly porous surfaces like matt painted walls, MDF etc.

MACal 9800 HT PRO provides ideal conformability over simple contours.

EXPECTED DURABILITY

The expected vertical outdoor durability of the unprocessed product in central Europe (Zone 1) is up to:

10 years : white and black.

This information is based on successful real life experience and artificial aging according to ISO 4892-2.

Note : Exposure to severe temperatures and ultraviolet light, as well as conditions in southern European countries, and also in tropical, sub-tropical or desert regions, will cause a more rapid deterioration. This also applies to polluted areas, high altitude, horizontal and south-facing exposure.

SHELF LIFE

2 years when stored at 15 to 25°C and ± 50 % relative humidity.

PHYSICAL PROPERTIES (Typical values)

Thickness (mm) (Film + adhesive) ISO 534
0.095

Face Material Data, 23°C DIN ISO 527-3

Tensile strength : ≥ 27 N/15mm

Elongation at break : ≥ 150 %

Adhesive Data, 23°C FTM 1

Peel adhesion 180° on stainless steel (N/25mm)

- 20 min. residence: 19

- 24 hours residence: 25

- 1 week residence: 27

Dimensional stability FTM 14

Shrinkage (1 week at 70°C) : < 0.5 mm

Temperature ranges :

Application : + 8°C to + 40°C

End-use : - 40°C to + 90°C

Flammability ISO 3795

Sample mounted on aluminium : self-extinguishing.

Solvent and chemical resistance

Resistant to most oils and grease, fuel, aliphatic solvents, weak acids, salts and alkalis.

PROCESSING

Computer cutting

Clean, quick, trouble-free cutting with most plotters. Adjustment of the cutting depth is important: if the cut is too deep this could result in the paper splitting and coming away with the adhesive when the vinyl is transferred to Application Tape.

Application

The transfer of the cut vinyl onto the Application Tape should always be performed by removing the liner from the pressure-sensitive material (i.e. with the PVC face downwards onto the working surface) and not by lifting off the Application Tape.

MACal 9800 HT PRO can be applied with the dry application method on slightly curved surfaces. On flat surfaces the dry or the wet application method is suitable.

Important remark

All surfaces to which the material will be applied must be thoroughly cleaned from dust, grease or any contamination. The compatibility of paints and lacquers should be tested by the end-user, prior to use.

Edge sealing and varnishing

Where exposure to chemicals and solvent spillage is likely to occur, edge sealing of decals with a varnish will prevent edge lift. Correct varnishing of decals gives greater protection, and extends the use-life against prolonged effects of weathering, abrasion and other effects such as frequent cleanings.

IMPORTANT NOTICE

All MACTac products are subject to careful quality control throughout the manufacturing process and are warranted to be of merchantable quality and free from manufacturing defects.

Published information concerning MACTac products is based upon research which the Company believes to be reliable although such information does not constitute a warranty.

Because of the variety of uses of MACTac products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. The seller shall not be liable for damages in excess of the purchase price of the product nor for incidental or consequential damages.

All specifications are subject to change without prior notice.